

The Following Chemicals are NOT Compatible with Polycarbonate Bowls

Acetaldehyde	Chloroform	Methylene chloride
Acetic acid	Cresol	Methylene salicylate
Acetone	Cyclohexanol	Milk of lime (CaOH ₂)
Acrylonitrile	Cyclohexanone	Nitric acid
Ammonia	Cyclohexene	Nitrobenzene
Ammonium fluoride	Dichlorobenzene	Nitrocellulose lacquer
Caustic soda solution	Dimethyl formamide	Perchloroethylene
Ammonium hydroxide	Dioxane	Phenol
Ammonium sulfide	Ethane tetrachloride	Phosphorous hydroxy chloride
Anaerobic adhesives	Ethyl alcohol	Phosphorous trichloride
Anaerobic sealants	Ethyl acetate	Propionic acid
Antifreeze	Ethyl ether	Pyridine
Benzene	Ethylamine	Sodium hydroxide
Benzoic Acid	Ethylene chlorohydrin	Sodium hypochlorite
Benzyl alcohol	Ethylene dichloride	Sodium sulfate
Brake fluids	Ethylene glycol	Styrene
Bromobenzene	Formic acid	Sulfuric acid
Butyric acid	Freon	Sulfuryl chloride
Carbolic acid	Formaldehyde	Tetrahydronaphthalene
Carbon disulfide	Gasoline	Thiophene
Carbon tetrachloride	Hydrazine	Toluene
Castor oil - Hydrogen	Hydrochloric acid	Trichloroethylene
Caustic potash solution	Lacquer thinner	Turpentine
Caustic soda solution	Methyl alcohol	Varnish
Chlorobenzene	Methyl ethyl ketone	Xylene

Please Note: This list does not contain all substances that can affect polycarbonate bowls. To ensure chemical compatibility, contact Coilhose Pneumatics for further information or compatibility questions.